


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	A_1	0.50000	72.00000	3.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		0.50000	72.00000	3.00000	10.00000
Mean		0.50000	72.00000	3.00000	10.00000
Median		0.50000	72.00000	3.00000	10.00000
Minimum		0.50000	72.00000	3.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.76398	10.593	8.82732	0.764	0.003
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.76398	10.593	8.82732	0.764	0.003
Mean	0.76398	10.593	8.82732	0.764	0.003
Median	0.76398	10.593	8.82732	0.764	0.003
Minimum	0.76398	10.593	8.82732	0.764	0.003
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	5568.67	8.827	10.593	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	5568.67	8.827	10.593	-----
Mean	5568.67	8.827	10.593	-----
Median	5568.67	8.827	10.593	-----
Minimum	5568.67	8.827	10.593	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----