


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	A_1	0.50000	72.00000	3.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		0.50000	72.00000	3.00000	10.00000
Mean		0.50000	72.00000	3.00000	10.00000
Median		0.50000	72.00000	3.00000	10.00000
Minimum		0.50000	72.00000	3.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	3.26646	16.484	13.73642	2.120	0.007
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	3.26646	16.484	13.73642	2.120	0.007
Mean	3.26646	16.484	13.73642	2.120	0.007
Median	3.26646	16.484	13.73642	2.120	0.007
Minimum	3.26646	16.484	13.73642	2.120	0.007
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	5369.69	13.736	16.484	2893.569
Coefficient of Variation	-----	-----	-----	-----
Maximum	5369.69	13.736	16.484	2893.569
Mean	5369.69	13.736	16.484	2893.569
Median	5369.69	13.736	16.484	2893.569
Minimum	5369.69	13.736	16.484	2893.569
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----