


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	A	1.00000	72.00000	3.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	3.00000	10.00000
Mean		1.00000	72.00000	3.00000	10.00000
Median		1.00000	72.00000	3.00000	10.00000
Minimum		1.00000	72.00000	3.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	7.53819	16.584	13.82023	2.196	0.008
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	7.53819	16.584	13.82023	2.196	0.008
Mean	7.53819	16.584	13.82023	2.196	0.008
Median	7.53819	16.584	13.82023	2.196	0.008
Minimum	7.53819	16.584	13.82023	2.196	0.008
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	5031.64	4.071	4.885	2778.403
Coefficient of Variation	-----	-----	-----	-----
Maximum	5031.64	4.071	4.885	2778.403
Mean	5031.64	4.071	4.885	2778.403
Median	5031.64	4.071	4.885	2778.403
Minimum	5031.64	4.071	4.885	2778.403
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----