


Flexure Test



Specimen Name
A_3

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	A_3	1.00000	72.00000	3.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	3.00000	10.00000
Mean		1.00000	72.00000	3.00000	10.00000
Median		1.00000	72.00000	3.00000	10.00000
Minimum		1.00000	72.00000	3.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	3.40291	11.708	9.75700	1.770	0.006
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	3.40291	11.708	9.75700	1.770	0.006
Mean	3.40291	11.708	9.75700	1.770	0.006
Median	3.40291	11.708	9.75700	1.770	0.006
Minimum	3.40291	11.708	9.75700	1.770	0.006
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	4163.25	9.757	11.708	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	4163.25	9.757	11.708	-----
Mean	4163.25	9.757	11.708	-----
Median	4163.25	9.757	11.708	-----
Minimum	4163.25	9.757	11.708	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----