


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	B_1	1.00000	72.00000	5.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	5.00000	10.00000
Mean		1.00000	72.00000	5.00000	10.00000
Median		1.00000	72.00000	5.00000	10.00000
Minimum		1.00000	72.00000	5.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.83220	20.379	47.17430	1.644	0.010
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.83220	20.379	47.17430	1.644	0.010
Mean	1.83220	20.379	47.17430	1.644	0.010
Median	1.83220	20.379	47.17430	1.644	0.010
Minimum	1.83220	20.379	47.17430	1.644	0.010
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	5768.21	34.291	14.814	730.700
Coefficient of Variation	-----	-----	-----	-----
Maximum	5768.21	34.291	14.814	730.700
Mean	5768.21	34.291	14.814	730.700
Median	5768.21	34.291	14.814	730.700
Minimum	5768.21	34.291	14.814	730.700
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----