


Flexure Test



Specimen Name
B_3

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	B_3	1.00000	72.00000	5.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	5.00000	10.00000
Mean		1.00000	72.00000	5.00000	10.00000
Median		1.00000	72.00000	5.00000	10.00000
Minimum		1.00000	72.00000	5.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	2.64150	11.236	26.00886	1.957	0.011
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	2.64150	11.236	26.00886	1.957	0.011
Mean	2.64150	11.236	26.00886	1.957	0.011
Median	2.64150	11.236	26.00886	1.957	0.011
Minimum	2.64150	11.236	26.00886	1.957	0.011
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	2318.66	25.868	11.175	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	2318.66	25.868	11.175	-----
Mean	2318.66	25.868	11.175	-----
Median	2318.66	25.868	11.175	-----
Minimum	2318.66	25.868	11.175	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----