


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	C_1	1.00000	72.00000	5.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	5.00000	10.00000
Mean		1.00000	72.00000	5.00000	10.00000
Median		1.00000	72.00000	5.00000	10.00000
Minimum		1.00000	72.00000	5.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.69966	26.743	61.90509	1.557	0.009
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.69966	26.743	61.90509	1.557	0.009
Mean	1.69966	26.743	61.90509	1.557	0.009
Median	1.69966	26.743	61.90509	1.557	0.009
Minimum	1.69966	26.743	61.90509	1.557	0.009
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	11082.80	23.763	10.266	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	11082.80	23.763	10.266	-----
Mean	11082.80	23.763	10.266	-----
Median	11082.80	23.763	10.266	-----
Minimum	11082.80	23.763	10.266	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----