


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	C_2	1.00000	72.00000	5.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	5.00000	10.00000
Mean		1.00000	72.00000	5.00000	10.00000
Median		1.00000	72.00000	5.00000	10.00000
Minimum		1.00000	72.00000	5.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.45714	20.645	47.78841	1.321	0.008
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.45714	20.645	47.78841	1.321	0.008
Mean	1.45714	20.645	47.78841	1.321	0.008
Median	1.45714	20.645	47.78841	1.321	0.008
Minimum	1.45714	20.645	47.78841	1.321	0.008
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	7799.87	23.789	10.277	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	7799.87	23.789	10.277	-----
Mean	7799.87	23.789	10.277	-----
Median	7799.87	23.789	10.277	-----
Minimum	7799.87	23.789	10.277	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----