


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	C_3	1.00000	72.00000	5.00000	10.00000
Coefficient of Variation		-----	-----	-----	-----
Maximum		1.00000	72.00000	5.00000	10.00000
Mean		1.00000	72.00000	5.00000	10.00000
Median		1.00000	72.00000	5.00000	10.00000
Minimum		1.00000	72.00000	5.00000	10.00000
Range		0.00000	0.00000	0.00000	0.00000
Standard Deviation		-----	-----	-----	-----

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.67298	27.773	64.28931	1.570	0.009
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.67298	27.773	64.28931	1.570	0.009
Mean	1.67298	27.773	64.28931	1.570	0.009
Median	1.67298	27.773	64.28931	1.570	0.009
Minimum	1.67298	27.773	64.28931	1.570	0.009
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	11058.17	23.723	10.248	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	11058.17	23.723	10.248	-----
Mean	11058.17	23.723	10.248	-----
Median	11058.17	23.723	10.248	-----
Minimum	11058.17	23.723	10.248	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----